

Attorney's Docket: 1999US001
Serial No.: 09/736/623
Group: 1751

Amendments to the Claims
1-15 (cancelled)

16. (previously presented) A textile treatment bath composition for pre-treating a cellulosic, or cellulosic blends with synthetic fiber, substrate prior to dyeing comprising:
- water;
 - a non-foaming scouring/wetting agent;
 - a first activating compound selected from the group of: salts of organic acids, a transitional metal, transitional metal salts, transitional metal complexes and combinations thereof;
 - optionally, a second activating compound selected from the group of: organic amine derivatives, pigments, and combinations thereof;
 - caustic soda; and
 - hydrogen peroxide;
- wherein said textile treatment bath composition starts with a pH greater than 9.7.

17. (previously presented) A textile treatment bath composition according to claim 16, wherein said first activating compound is a salt of an organic acid is selected from sodium salts of citric acid, sodium stearate, sodium salts of gluconic acid, sodium oleate, potassium salt of citric acid, potassium stearate, potassium salt of gluconic acid, potassium oleate, ammonium salts of citric acid, ammonium stearate, ammonium salts of gluconic acid, ammonium oleate, and combinations thereof.

18. (previously presented) A textile treatment bath composition according to claim 17, wherein said salt of organic acid is about 0.2 to about 5.0% based on the weight of the substrate.

Attorney's Docket: 1998US001
Serial No.: 09736.523
Group: 1751

18. (previously presented) A textile treatment bath composition according to claim 16, wherein said second activating compound is an organic amine derivative selected from urea, dicyandiamide, tetra-acetyl-ethylene-di-amine, acetyl-caprolactam, and combinations thereof.

20. (previously presented) A textile treatment bath composition according to claim 19, wherein said organic amine derivative is about 0.2 to about 5.0% w/w.

21. (previously presented) A textile treatment bath composition according to claim 16, wherein said first activating compound is a transitional metal complex selected from copper gluconate, copper sulfate, copper acetate, copper carbonate, copper citrate, copper nitrate, copper EDTA, copper complexes, and combinations thereof.

22. (previously presented) A textile treatment bath composition according to claim 21, wherein said transitional metal is about 0.1 to about 10ppm based on the weight of the bath.

23. (previously presented) A textile treatment bath composition according to claim 16, wherein said second activating compound is a pigment selected from pigmented Sulfur Black 1 with a particle size less than 150µm, titanium dioxide with a particle size less than 150µm, fully pre-oxidized sulfur dyes, and combinations thereof.

24. (previously presented) A textile treatment bath composition according to claim 23, wherein said pigment is selected from Dinesul Black 4G-EV and Titanium Dioxide.

25. (previously presented) A textile treatment bath composition according to claim 23, wherein said pigment is about 1 to about 200 ppm w/w.

Attorney's Docket: 1989US001
Serial No.: 08738,623
Group: 1751

26. (previously presented) A textile treatment bath composition according to claim 16, wherein said non-foaming scouring/wetting agent is selected from ethoxylated fatty alcohol and propoxylated fatty alcohol.

27. (previously presented) A textile treatment bath composition according to claim 26, wherein said non-foaming scouring/wetting agent is about 0.1 to about 1.5% owg.

28. (previously presented) A textile treatment bath composition according to claim 16 further comprising a peroxide stabilizer.

29. (previously presented) A textile treatment bath composition according to claim 28, wherein said peroxide stabilizer is selected from an organo-phosphate based agent, an amino-organic acid based agent, an organic acid based agent, a polyacrylic acid based agent, an earth alkaline salt, and combinations thereof.

30. (previously presented) A textile treatment bath composition according to claim 29, wherein said organo-phosphate based agent is Diethylenetriamine penta(methylene phosphonic acid), said amino-organic acid based agent is Diethylenetriamine pentaacetic acid, said organic acid based agent is Sodium salt of Gluconic Acid, and said earth alkaline salt is Mg^{+2} salt.

31. (previously presented) A textile treatment bath composition for pre-treating a cellulosic, or cellulosic blends with synthetic fiber, substrate prior to dyeing comprising:
at least 90% water;
a non-foaming scouring/wetting agent;
a first activating compound formed of a mixture of urea and copper gluconate;

Attorney's Docket: 1998US001
Serial No.: 09738,823
Group: 1761

optionally, a second activating compound selected of a pigment;

caustic soda; and

hydrogen peroxide;

wherein said textile treatment bath composition starts with a slightly alkaline pH.

32. (previously presented) A textile treatment bath composition according to claim 31, wherein said second activating compound is a pigment selected from pigmented Sulfur Black 1 with a particle size less than 150µm, titanium dioxide with a particle size less than 150µm, fully pre-oxidized sulfur dyes, and combinations thereof.

33. (cancelled)

34. (cancelled)

35. (previously presented) A textile treatment bath composition for pre-treating a cellulosic, or cellulosic blends with synthetic fiber, substrate prior to dyeing comprising:

at least 90% water;

a non-foaming scouring/wetting agent;

a salt of an organic acid;

caustic soda; and

hydrogen peroxide;

wherein said textile treatment bath composition starts with a pH greater than 9.7.

36. (previously presented) A textile treatment bath composition for pre-treating a cellulosic, or cellulosic blends with synthetic fiber, substrate prior to dyeing according to claim 35.

Attorney's Docket: 1998US001
Serial No.: 08/738,623
Group: 1781

with the further addition of tetraacetyl ethylenediamine.

37. (previously presented) A cellulosic, or cellulosic blends with synthetic fiber, substrate that has been prepared for dyeing by a treatment bath comprising:
- at least 90% water;
 - a non-foaming scouring/wetting agent;
 - a first activating compound selected from the group of: salts of organic acids, a transitional metal, transitional metal salts, transitional metal complexes and combinations thereof;
 - optionally, of a second activating compound selected from the group of: organic amine derivatives, pigments, and combinations thereof;
 - caustic soda; and
 - hydrogen peroxide;
- wherein said textile treatment bath composition starts with a pH greater than

9.7.

38. (previously presented) A textile treatment bath composition for pre-treating a cellulosic, or cellulosic blends with synthetic fiber, substrate prior to dyeing comprising:
- at least 90% water;
 - a non-foaming scouring/wetting agent;
 - a first activating compound selected from the group of: salts of organic acids, a transitional metal, transitional metal salts, transitional metal complexes and combinations thereof;

Sulfur Black 1 as a second activating compound;

- caustic soda; and
- hydrogen peroxide;

wherein said textile treatment bath composition starts with a pH greater than

9.7.

Attorney's Docket: 1999US001
Serial No.: 08730.523
Group: 1751

30. (previously presented) A textile treated with the textile treatment bath composition of claim 31, wherein the textile is selected from the group consisting of cellulosic textiles and cellulosic blends with synthetic fiber textiles.

4D. through 50. (cancelled)